


KEY RESIN COMPANY



KEY ELECTRO-STATIC DISSIPATIVE WATER EMULSION FINISH #535-ESD

DESCRIPTION

KEY RESIN #535-ESD is a pigmented, water emulsion epoxy electro-static dissipative finish designed to have maximum penetration into concrete surfaces to provide high bond strength and adhesion. **KEY RESIN #535-ESD** has very low odor and can be used in occupied areas as a finish sealer in **Thin-Film Electro-Static Dissipative Coating Systems**.

APPLICATION

SURFACE PREPARATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared as outlined in **KEY RESIN COMPANY'S TECHNICAL BULLETIN #1**. Work must be performed by trained or experienced contractors or maintenance personnel. The **KEY RESIN COMPANY** service department is pleased to answer any questions.

INSTALLATION

Mix each component of **KEY RESIN #535-ESD** prior to combining. Mix 1 part Part A with 4 parts Part B and allow to stand 15-30 minutes before applying. Roll mixed **KEY RESIN #535-ESD** at a rate of 275-300 ft² per gallon with a short nap roller. Care should be taken to avoid puddles. Do not build a film of the sealer and roll out so that it soaks into the concrete. Two coats are necessary to insure uniform wetting and coverage. For complete installation instructions, contact your **Key Representative** or **Key Resin Company's Technical Service**.

CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with xylene or lacquer thinner. Consult Material Safety Data for safety and health precautions.

COMPOSITION

Waterborne Epoxy Resin and Conductive Fillers

KEY ADVANTAGES

- Low Odor During Application and Cure
- Fast Dry and Re-coat Time
- Easy Clean-up
- Can be used on Damp/Green Concrete
- Greatly Reduces the Probability of Concrete Outgassing
- Provides a conductive finish in the range of 1,000,000 to 1,000,000,000 ohms resistance

KEY CONSIDERATIONS

- Substrate temperature must be a minimum of 50°F and relative humidity below 85% for proper curing
- Substrate must be free of dirt, waxes, curing agents, and other foreign materials

COLOR SELECTION

KEY RESIN #535-ESD is available in most **Key Standard Colors**. Contact your **Key Representative** for assistance.

COVERAGE

KEY RESIN #535-ESD, when applied at 300 ft², yields 2-2.5 mils dry film.

TECHNICAL DATA

Viscosity @ 75°F	300-400 cps
Mixing Ratio	1 Part A to 4 Parts B by Volume
Solids Content	40-45%
Volatile Organic Content (VOC)	<60 gm/L
Bond Strength to Concrete	400-500 psi (100% concrete failure)
Weight per Gallon	8.75-9.00 pounds per gallon, mixed

CURE/DRY TIME

Pot Life	2-4 hours
Dry to Touch	4-6 hours @ 75°F
Re-Coat	6-24 hours @ 75°F
Light Traffic	24 hours @ 75°F
"H" Hardness	2 days
"5-H" Hardness	30 days

AVAILABILITY

Key Resins are available throughout the United States, Canada, and a number of other countries. Contact the **KEY REPRESENTATIVE** in your area for details.

MAINTENANCE

After completing the application of **KEY RESIN #535-ESD**, the installer should provide the owner with maintenance instructions. If floors become slippery due to animal fats, oil, grease, or soap film, clean and rinse thoroughly.

KEY RESIN #535-ESD is easily cleaned with neutral soaps or detergents. Routine mechanical scrubbing is recommended for all surfaces having a non-skid texture. Waxing is optional. Long periods of heavy traffic may cause wear patterns necessitating a maintenance application of a finish coat.

TECHNICAL SERVICE

Key Resin Company and **KRC Associates, Inc.** provide services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces. **KEY REPRESENTATIVES** are available to assist you at any time. CALL (888)943-4532.

WARRANTY Key Resin Company ("Key") warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed and applied in accordance with recommendations of Key. If any product fails to meet this warranty, the liability of Key will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Key within (1) one year of delivery of materials. Key may in its discretion refund the price received by Key in lieu of replacing the material. No customer, distributor, or representative of Key is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Key. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Key reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. KEY'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND KEY SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



Key #535-ESD-2