


KEY RESISTANT STD

Technical Data Sheet



DESCRIPTION

KEY RESISTANT STD provides the maximum chemical resistance in a 1/4" troweled epoxy mortar system. Combining a 100% solids, chemically resistant mortar base with chemical resistant epoxy or novolac epoxy sealers, **KEY RESISTANT STD** protects concrete and masonry where extreme chemical and thermal protection is required. **KEY RESISTANT STD** can be installed with an integral cove base for areas requiring seamless wall to floor coatings. A waterproof, crack resistant system can be achieved by using a **KEY CRACK ISOLATION AND WATERPROOFING MEMBRANE**. Contact your **KEY REPRESENTATIVE** for assistance.

KEY ADVANTAGES

- High wear, impact, & abrasion resistance
- Extreme chemical & thermal shock resistance
- Low maintenance
- Safe (slip resistant finish)
- 100% solids provides low odor application
- Authorized for use in federally inspected meat and poultry plants

TYPICAL USES

- Pulp and Paper Plants
- Food and Beverage Facilities
- Pulp and Paper Mills
- Petroleum and Chemical Plants
- Pharmaceutical Facilities
- Wastewater Treatment Facilities
- Numerous other uses-Consult with Key Resin

PHYSICAL PROPERTIES

Test Name	Method	Value
Color		Key Standard Colors and Custom Colors
VOC (Volatile Organic Content)	EPA Method 24	Refer to Individual Product Component Data Sheet
Adhesion to Concrete	ASTM D7234	300-400+ psi Concrete Failure
Compressive Strength	ASTM C579	15,000 psi
Flexural Strength	ASTM C580	3,700 psi
Hardness, Shore D	ASTM D2240	80-85
Tensile Strength	ASTM D638	6,000 psi
Flammability	ASTM D635	Self Extinguishing
Abrasion Resistance	ASTM D4060, CS17 Wheel, 1000 cycles	80-100 mg lost
Impact Resistance	MIL-D-3134J	Withstands 16 ft-lbs without cracking, delamination or chipping
Resistance to Elevated Temperatures	MIL-D-3134J	No slip or flow at required temperature of 158°F
Slip Resistance	ASTM D2047	>0.6 Passes ADA recommendations

KEY RESISTANT STD

Technical Data Sheet



APPLICATION

SURFACE PREPARATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared and tested for moisture as outlined in **Key Resin Technical Bulletin #1**. If moisture testing confirms excessive levels of moisture, apply moisture mitigation system recommended by **Key Resin**. Work must be performed by experienced contractors. The **Key Resin Technical Service Department** is available to answer any questions.

INSTALLATION

KEY RESISTANT STD material components are mixed on site. Refer to the detailed installation instructions document and **Key Resin Technical Service**.

CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with xylene or lacquer thinner. Consult Safety Data Sheet (SDS) for safety and health precautions.

MAINTENANCE

After completing the application of the **KEY RESISTANT STD SYSTEM**, the installer should provide the owner with maintenance instructions. **KEY RESISTANT STD** is easily cleaned with neutral soaps or detergents. Routine mechanical scrubbing using the appropriate pad is recommended for all surfaces having a slip resistant texture. Refer to **Key Resin Technical Bulletins #3 and #3-A** for additional recommendations.

WARRANTY

Key Resin Company ("Key") warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed, and applied in accordance with recommendations of Key. If any product fails to meet this warranty, the liability of Key will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Key within (1) one year of delivery of materials. Key may in its discretion refund the price received by Key in lieu of replacing the material. No customer, distributor, or representative of Key is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Key. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Key reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. KEY'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND KEY SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

SYSTEM OPTIONS

- Integral Cove Base
- Key Crack Isolation and Waterproofing Membrane
- Smooth or Slip Resistant Finish

TECHNICAL SERVICE

Key Resin Company provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces. **Key Resin Sales/Technical Representatives** are available to assist. Telephone 888.943.4532 or visit www.keyresin.com.

AVAILABILITY

Key Resin materials are available throughout the United States, Canada, China, and a number of other countries. Contact the **Key Resin Representative** in your area for details.

