

# KEY URECON TG

## Product Information Sheet



## DESCRIPTION

**KEY URECON TG** is a 1/4"-3/8" heavy duty, trowel applied urethane modified cementitious topping. Ideal for heavy duty traffic areas, **KEY URECON TG** exhibits high impact resistance and excellent thermal shock and chemical resistance. **KEY URECON TG** is a moisture vapor tolerant system making it the ideal solution for many moisture problems. **KEY URECON TG** may be used both indoors and outdoors and in areas where freeze/thaw is a factor. Its textured surface reduces slipping under most wet conditions. Excellent for rehabbing old floors, **KEY URECON TG** provides a much stronger, longer lasting, and attractive surface. **KEY URECON TG** is the key choice for wet areas, dairies, food processing areas, and industrial kitchens. **KEY URECON TG** can be installed with an integral cove base for areas requiring seamless wall to floor systems, it will not support the growth of fungus or bacteria.

## KEY ADVANTAGES

- High impact, thermal shock, and wear resistance
- Excellent chemical resistance
- Low odor for use in occupied areas
- Meets USGBC LEED criteria for low VOC
- Hygienic—will not support growth of fungus or bacteria
- Moisture vapor tolerant system; up to 95% RH probe test and 15 lbs calcium chloride test
- Chemical resistant sealers are available
- Meets USDA requirements
- Rapid one step application for fast return to service

## KEY CONSIDERATIONS

- Should be applied when temperature is between 50°F and 85°F
- Site must be free from condensation or water contamination during application and cure
- Concrete substrate must be free of dirt, waxes, curing agents, and other foreign materials
- Expansion joints in the substrate must be revealed through the topping and filled with urethane sealant
- Movement of substrate cracks may transmit through system

## COLOR SELECTION

Refer to **Key Dry Oxide Pigment Colors Chart**. Price surcharge for Dark/Light Blue, Green. May also use **Key Urethane Pigment Packs** at additional cost. Light colors may become altered with exposure to UV spectrum light.

## CURE/DRY TIME

Working Life	10-15 mins @ 75°F, 50% RH
Recoat* (*Accelerator Additive reduces time)	6-8 hrs @ 75°F, 50% RH
Light Foot Traffic Service	8-10 hrs @ 75°F, 50% RH
Light Vehicular Traffic	12-16 hrs @ 75°F, 50% RH
Full Cure & Max. Resistance	3-5 days @ 75°F, 50% RH

## APPLICATION

### SURFACE PREPARATION

Surface Preparation is the most critical portion of any successful resinous flooring system application. All substrates must be properly prepared as outlined in **Key Resin Technical Bulletin #1**. Work must be performed by trained or experienced contractors or maintenance personnel. The **Key Resin Technical Service Department** is available to answer any questions.

### MIXING INSTRUCTIONS

Mechanical mixing is required. Add Part I and Part II in running mixer and blend until uniform (about 30 seconds). Add Part III aggregate and pigment pack slowly to mix and blend for 1 more minute. Use immediately.

### INSTALLATION

**KEY URECON TG** is installed using a steel trowel. Refer to detailed installation instructions document and **Key Resin Technical Service** for additional important details.

### CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with xylene or lacquer thinner. Consult Safety Data Sheet (SDS) for safety and health precautions.

## MAINTENANCE

After completing the application of **KEY URECON TG**, the installer should provide the owner with maintenance instructions. **KEY URECON TG** is easily cleaned with neutral soaps or detergents. Refer to **Key Resin Technical Bulletin #3** and **#3A** for additional recommendations.

## COMPOSITION

**KEY URECON TG** is a urethane modified, portland cement system blended with a variety of graded silica, or ceramic fillers.

# KEY URECON TG

## Product Information Sheet



### TECHNICAL DATA

Mixing Ratio	Pre-Packaged Kit
Weight (liquids)	9.00-9.50 lbs per gallon, mixed
Volatile Organic Content (VOC) (EPA Method 24)	0 g/L, compliant to low VOC Rule 1113 in all 50 states

### PHYSICAL PROPERTIES

Flammability	ASTM D635	Self-Extinguishing
Fungus and Bacteria Growth	MIL-F-52505 § 4.4.2.11	Will not support growth of fungus or bacteria when subjected to mildew and bacteria tests
Hardness, Shore D	ASTM D2240	80-85
Adhesion to Concrete	ASTM D7240	300-400+ psi (Concrete Failure, varies by concrete strength)
Flexural Strength	ASTM C580	2,000 psi
Coefficient of Friction	ASTM D2047	0.80
Water Absorption	ASTM D570	0.10%
Thermal Shock Resistance	ASTM C884	Passes
Abrasion Resistance	ASTM D4060 CS17 Wheel, 1000 cycles	50 mgs
Impact Resistance	MIL-F-3134J	Withstands 16 ft./lb. without cracking, delamination, or chipping
Compressive Strength	ASTM C579, 7 days	7,500 psi
Tensile Strength	ASTM C307	800 psi
Thermal Coefficient of Expansion	ASTM C531	1.1 x 10 <sup>-5</sup> in/in/per °F
Service Temperature Resistance		-50 – 240°F wet, 280°F wet intermittent, 350°F dry

### AVAILABILITY

Key Resin materials are available throughout the United States, Canada, and a number of other countries. Contact the **Key Resin Representative** in your area for details.

### TECHNICAL SERVICE

Key Resin Company provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces. **Key Resin Sales/Technical Representatives** are available to assist you. Telephone 888.943.4532 or visit [www.keyresin.com](http://www.keyresin.com).

### WARRANTY

Key Resin Company ("Key") warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed, and applied in accordance with recommendations of Key. If any product fails to meet this warranty, the liability of Key will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Key within (1) one year of delivery of materials. Key may in its discretion refund the price received by Key in lieu of replacing the material. No customer, distributor, or representative of Key is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Key. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Key reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. KEY'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND KEY SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

