

Technical Bulletin #38-B Key Conductive Epoxy Electrical Resistance Testing

Key Resin Conductive Epoxy Flooring Systems provide a flooring surface that exhibits resistivity readings between 25,000 and 1,000,000 ohms when tested in accordance with ANSI/ESD Association S7.1. The testing of the floor surface is accomplished through the use of a megohmmeter and weighted floor electrodes, also referred to as a digital resistance/resistivity test meter.



Point-to-Point Resistance Testing Procedure:

- Allow the Key Resin Conductive Epoxy Flooring System to cure for a minimum of 72 hours (at 75°F) before testing. It must not have any sealers or wax finish on the surface. During the test procedure, temperature and air relative humidity should be ambient conditions.
- The flooring surface should be clean. If necessary, clean floor thoroughly with damp mop using neutral detergent, rinsing with clean water. Refer to Key Resin Technical Bulletin #3 “General Care and Maintenance Instructions of Key Resin Flooring Systems”. Allow to dry completely.
- Clean electrodes with a minimum 70% isopropanol-water solution using a clean, low-linting cloth. Allow electrode to air dry.
- Place the floor electrodes 3 feet apart and apply the test voltage in accordance with the particular meter’s instructions. A meter with auto capabilities will select the correct output voltage and duration of test. If the meter has only a manual mode, set voltage to 10 volts and hold for 15 seconds, then record value.
- Key Resin Conductive Epoxy Flooring Systems should test between 2.5×10^4 and 1.0×10^6 ohms. Consult with Key Resin Technical Service if readings fall outside of this range. If any readings exceed 1.0×10^6 ohms, set meter to 100 volts and retest.

KEY RESIN COMPANY TECHNICAL BULLETIN



- Perform a minimum of 5 tests (in different locations) per contiguous floor surface material or a minimum of 5 tests per 5000 ft², whichever is greater.
- Report all values in ohms for resistance point-to-point. Report test voltage, test date, temperature, and relative humidity at time of testing, actual duration of environmental conditioning, and test equipment used. Summarize test data by reporting the minimum, maximum, mean, and median values obtained. Include a diagram showing approximate electrode positions used.

Point-to-Ground Resistance Testing Procedure:

- If the Key Resin Conductive Epoxy Flooring System has been connected to a building ground point, place one electrode on the floor, and use the other cord with alligator clip accessory and attach it to building ground point near where the floor has been grounded. Run test as outlined above and record values.

REV 08/27/21 v1.0

CORPORATE - 888.943.4532
4050 Clough Woods Drive, Batavia, OH 45103

WESTERN US – 602.523.9353
4330 N 43rd Ave, Suite B-4, Phoenix, AZ 85031