

Flowseal EPW (6 - 8 mils)*

A vapor permeable, water-dispersed epoxy floor coating system available in a range of neutral shades.



Vapor Permeable:

Fully breathable and can be installed onto damp substrates or green concrete.



Solvent Free:

Water dispersed epoxy resin technology free from solvents and VOCs.



Easily Mixed & Applied:

Easily mixed and applied using a roller or rubber squeegee.



Low Maintenance:

End of life surfaces can be over-coated with minimal surface preparation.



Seamless & Easily Cleaned:

Seamless installation ensures dirt and dust are swiftly and easily cleaned away.

Standard Colors:

100 Light Grey	135 Medium Grey	170 Dark Grey	185 Charcoal
210 White Sand	300 Taupe	435 Tan	440 Khaki
480 Beige	550 Green	600 Slate Blue	650 Light Blue
750 Blue	980 Red	850 Traffic Yellow	950 Traffic Red

SLIP RESISTANCE: PTV BS 7976-2 (Using TRRL Rubber Wet: Dependent on Slider) ABRASION RESISTANCE: ASTM D 4060 0.050g loss CS 17 Wheel, 1000 cycles VAPOR PERMEABILITY: ASTM E 96 20g/m²/mm/24 hrs **BOND STRENGTH:** Greater than cohesive strength of 3,000 psi concrete, > 220 psi **SURFACE HARDNESS:** Koenig Hardness Test >180 secs **TEMPERATURE RESISTANCE:** Continuous Exposure: Up to 140°F VOC: 26 g/l **VOLUME SOLIDS:** Approx. 50% **SPEED OF CURE:** 50°F 70°F 90°F Light Traffic **Full Traffic** Full Chemical Cure Flowseal EPW Prepared Substrate

Products Included In This System

1st Coat: Flowseal EPW at 225 sq ft/gal
2nd Coat: Flowseal EPW at 225 sq ft/gal

Typical values, application and coverage rates are assisted by the addition of water - up to maximum of 16 oz per unit.

Coverages listed are theoretical, coverages may vary based on substrate and site variations. For optional slip resistant dressings please consult our Technical Advisors.

Installation

Installation should be carried out by a Key Resin
Company preferred contractor with a documented
quality assurance note. Obtain details of our preferred
contractor network from our customer service team or
by enquiring through our website. Detailed application
instructions are also available upon request.

Substrate Requirements

Concrete or screed substrate should have a minimum of 3,000 psi compressive strength, free from laitance, dust and other contamination. The substrate should be dry to ASTM requirements and free from excessive moisture vapor transmission.

Technical Profile

The figures and test results shown overleaf are typical properties achieved in laboratory tests at 75°F and at 50% Relative Humidity.

Aftercare, Cleaning & Maintenance

Clean regularly using a single or double headed rotary scrubber / drier with a mildly alkaline detergent.

Environmental Health & Safety

The finished system is assessed as non-hazardous to health and the environment. The long service life and seamless surface reduce the need for repairs and maintenance. Environmental and health considerations are controlled during manufacture and application of the products by Key Resin Company staff and fully trained application teams.

Warranty

Key Resin Company products are guaranteed against defective materials and manufacture and are sold subject to our standard 'Warranty, Terms and Conditions of Sale', copies of which can be obtained on request. Warranty does not cover suitability, fit for purpose or any consequential or related damages. Please review warranty in detail before installing the products.

Disclaimer

Any recommendation or suggestion relating to the use of products manufactured by Key Resin Company, whether in its technical literature or in response to a specific inquiry, is based upon data believed to be reliable, however the products and information are intended for use by applicators having requisite skill and know-how in the industry and therefore it is for the applicator to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that the applicator has done so at its sole discretion and risk.

[01/17/22] FlowResin

AIA