KEY #783 EPOXY NOVOLAC JOINT FILLER

Product Data Sheet



DESCRIPTION

KEY #783 is a 100% solids, semi-rigid epoxy novolac joint filler used to provide chemical resistant protection for saw-cut joints (contraction/control joints) in concrete slabs or to repair existing damaged joints. **KEY #783** absorbs the impact and shock of heavy loads and steel wheeled traffic, preventing erosion of control joint edges.

KEY ADVANTAGES

- Easy 1 to 1 mix ratio
- Ultimate elongation of 80-100%
- · Low odor for use in occupied areas
- Meets USGBC LEED criteria for low VOC
- · Chemical resistant

KEY CONSIDERATIONS

- Substrate temperature must be a minimum of 50°F
- Substrate must be free of dirt, waxes, curing agents, and other foreign materials
- Follow ACI guidelines, should not be installed on new concrete cured <30 days

COLOR SELECTION

Gray. Custom colors available subject to lab approval, additional lead time and cost.

COMPOSITION

100% solids epoxy novolac resin with aliphatic amines.

CURE/DRY TIME

Working Life	40 minutes @ 75°F
Dry to Touch	6-8 hours @ 75°F
Recoat	8-10 hours @ 75°F
Sanding Time	24-48 hours @ 75°F
Full Cure & Maximum Resistance	48-72 hours @ 75°F

APPLICATION

SURFACE PREPARATION

Surface Preparation is the most critical portion to any successful resinous flooring system application. All substrates must be properly prepared as outlined in **Key Resin Technical Bulletin #1**. Work must be performed by trained or experienced contractors or maintenance personnel. The **Key Resin Technical Service Department** is available to answer any questions.

MIXING and INSTALLATION

KEY #783 is mixed by combining equal parts by volume of Part A and Part B. Pre-mix each component prior to combining. Mix combination with a low speed drill for a minimum of three minutes.

KEY #783 can be poured from a suitable container or applied with a caulking gun. Two passes may be required as pourable materials have a tendency to "dish out". The filled joint MUST be flush with the floor. For complete installation instructions, contact **Key Resin Technical Service**.

COVERAGE Linear Feet / Gallon

$Width {\rightarrow}$							
Depth↓	1 /8"	1/4"	3/8"	1/2"	5/8"	3/4"	1"
1/4"	616.0	308.0	205.3	154.0	123.2	102.7	77.0
1/2"	308.0	154.0	102.7	77.0	61.6	51.3	38.5
3/4"	205.3	102.7	68.4	51.3	41.1	34.2	25.7
1"	154.0	77.0	51.3	38.5	30.8	25.8	19.3
1 1/4"	123.2	61.6	41.1	30.8	24.6	20.5	15.4
1 1/2"	102.7	51.3	34.2	25.7	20.5	17.1	12.8
1 3/4"	88.0	44.0	29.3	22.0	17.6	14.7	11.0
2"	77.0	38.5	25.7	19.3	15.4	12.8	9.6
1 1/2"	61.6	30.8	10.5	14.7	12.3	10.3	7.7
2 3/4"	51.3	25.7	17.6	12.8	10.3	8.6	6.4

CLEAN UP

Clean skin with soap and water. Tools and equipment should be cleaned with xylene or lacquer thinner before **KEY #783** gels. Consult Safety Data Sheet (SDS) for safety and health precautions.

KEY #783 EPOXY NOVOLAC JOINT FILLER

Product Data Sheet



TECHNICAL DATA

Mixing Ratio	1 Part A to 1 Part B by Volume
Volatile Organic Content (VOC) (EPA Method 24)	0 g/L, compliant to low VOC Rule 1113 in all 50 states
Solids Content	100% Solids by Volume
Weight	10.50 lbs/gal, mixed
Viscosity	2,200 cps

PHYSICAL PROPERTIES

Artificial Weathering Type D 10-15% elastomer property change after 1,000 hrs Bond Cohesion after Water Immersion Fed Spec TT-S-00227E No failure after 25% total movement Bond Strength to Concrete ASTM D7243 300+ psi Concrete failure, varies by concrete strength Service Temperature 30-180°F Tear Resistance ASTM D624-73 30 lb/in Tensile Strength ASTM D638 600 psi Ultimate Elongation This property provided only for comparison with other fillers. Elongation does not directly correlate to lateral expansion capability. Hardness ASTM D2240 80-85 Shore A 30-40 Shore D		=:::::	. •
Water Immersion TT-S-00227E total movement Bond Strength to Concrete ASTM D7243 Service Temperature Tear Resistance ASTM D624-73 30 lb/in Tensile Strength ASTM D638 600 psi Ultimate Elongation This property provided only for comparison with other fillers. Elongation does not directly correlate to lateral expansion capability. Hardness ASTM D2240 80-85 Shore A	Artificial Weathering		property change
Concrete Concrete failure, varies by concrete strength Service Temperature 30-180°F Tear Resistance ASTM D624-73 30 lb/in Tensile Strength ASTM D638 600 psi Ultimate Elongation This property provided only for comparison with other fillers. Elongation does not directly correlate to lateral expansion capability. Hardness ASTM D2240 80-85 Shore A	20114 0011001011 41101		
Tear Resistance ASTM D624-73 30 lb/in Tensile Strength ASTM D638 600 psi Ultimate Elongation This property provided only for comparison with other fillers. Elongation does not directly correlate to lateral expansion capability. Hardness ASTM D2240 80-85 Shore A		ASTM D7243	Concrete failure, varies by
Tensile Strength ASTM D638 600 psi Ultimate Elongation This property provided only for comparison with other fillers. Elongation does not directly correlate to lateral expansion capability. Hardness ASTM D2240 80-85 Shore A	Service Temperature		30-180°F
Ultimate Elongation This property provided only for comparison with other fillers. Elongation does not directly correlate to lateral expansion capability. Hardness ASTM D2240 80-85 Shore A	Tear Resistance	ASTM D624-73	30 lb/in
This property provided only for comparison with other fillers. Elongation does not directly correlate to lateral expansion capability. Hardness ASTM D2240 80-85 Shore A	Tensile Strength	ASTM D638	600 psi
7.0.1 <u>2</u>	This property provided only for comparison with other fillers. Elongation does not directly correlate to lateral expansion	ASTM D638	80-100%
	Hardness	ASTM D2240	

MAINTENANCE

KEY #783 is typically installed as a joint material for **Key Resin Flooring Systems.** However, if needed **KEY #783** can be cleaned with neutral soaps and detergents.

AVAILABILITY

Key Resin materials are available throughout the United States, Canada, and a number of other countries. Contact the **Key Resin Representative** in your area for details.

TECHNICAL SERVICE

Key Resin Company provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces. **Key Resin Sales/Technical Representatives** are available to assist you. Telephone 888.943.4532 or visit www.keyresin.com.

WARRANTY

Key Resin Company ("Key") warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed, and applied in accordance with recommendations of Key. If any product fails to meet this warranty, the liability of Key will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Key within (1) one year of delivery of materials. Key may in its discretion refund the price received by Key in lieu of replacement and its occurrence of the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Key. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Key reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANT-ABILITY OR FITNESS FOR PURPOSE. KEY'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND KEY SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Rev 6/26/2020 v1.0