

KEY #511-UV EPOXY

Product Data Sheet



DESCRIPTION

KEY #511-UV is a clear, UV light resistant general purpose epoxy resin for use as primer, slurry binder, trowel mortar binder, broadcast systems, and coating applications. This resin has excellent clarity compared to standard epoxy formulations. It is essentially odorless and can therefore be used in occupied buildings. **KEY #511-UV** provides increased barrier thickness and gives added protection to concrete against chemical and abrasive attack.

KEY ADVANTAGES

- Convenient 2:1 mixing ratio
- Meets USGBC LEED criteria for low VOC
- Low odor for use in occupied areas
- Greater resistance to indoor UV light ambering (Clear only)
- Low viscosity - good wetting properties
- Available in "fast cure" formulation
- Available in Clear, may be tinted with Universal Color Packs.
- Meets USDA standards for incidental food contact

KEY CONSIDERATIONS

- Recommended minimum application temp. of 60°F
- Substrate must be free of curing agents and any foreign materials
- On or below grade installation must have an efficient vapor barrier directly under the slab
- Special treatments are necessary where moisture vapor emissions may be present. Contact **Key Resin** for proper MVT treatments

COLOR SELECTION

KEY #511-UV is available in Clear only, may be tinted with UNVCP Universal Color Packs in Key Resin Standard Colors EXCEPT DO NOT use the following: 750 Blue, 185 Charcoal, decreased hardness will result.

COMPOSITION

100% solids Amine Cured Epoxy Resin.

COVERAGE

KEY #511-UV coverage rate will vary by application method. Typical thickness as a sealer is 10-20 mils.

CURE/DRY TIME

Working Life	30 minutes @ 70°F
Recoat Time	12-24 hrs @ 70°F
Light Foot Traffic	16-18 hrs @ 70°F
Ultimate Cure @ 75°F	5-7 days
Ultimate Cure @ 50°F	14 days

APPLICATION

SURFACE PREPARATION

Surface Preparation is the most critical portion to any successful resinous flooring system application. All substrates must be properly prepared as outlined in **Key Resin Technical Bulletin #1**. Work must be performed by trained or experienced contractors or maintenance personnel. The **Key Resin Technical Service Department** is available to answer any questions.

INSTALLATION

Will vary with system and application method.

CHEMICAL RESISTANCE

REAGENT	RATING
Acetic Acid - 5%	L
Acetone	L
Bleach	L
Citric Acid - 30%	L
Crude Oil	R
Diesel Fuel	R
Ethylene Glycol	R
Fatty Acids	L
Gasoline	R
Hydrochloric Acid - 15%	R
Lactic Acid - 15%	L
Methyl Ethyl Ketone	L
Nitric Acid - 10%	L
Skydrol	R
Sodium Hydroxide - 50%	R
Sulfuric Acid - 20%	L
Toluene	R
Urea	R
Vinegar	L
Xylene	R

R - Recommended for splash/spill service with daily cleanup.

L - Limited recommendation for 8 hours or less exposure time, requires more frequent cleanup, occasional spills only. Bleach or acids allowed to evaporate/concentrate repeatedly will cause stains or discoloration depending on exposure time. Increase in exposure time increases the concentration and reactivity of the reagent.

KEY #511-UV EPOXY

Product Data Sheet



TECHNICAL DATA

Mix Ratio	2 Parts A:1 Part B by Volume
Weight/gal	8.5-9 lbs. Mixed
Solids Content	Approximately 100%
Volatile Organic Content (VOC) (EPA Method 24)	<50 g/L, compliant to low VOC Rule 1113 in all 50 states
Gloss, 60°	85-100
Viscosity	400-600 cps, mixed approx.

AVAILABILITY

Key Resin materials are available throughout the United States and a number of other countries. Contact the **Key Resin Representative** in your area for details.

TECHNICAL SERVICE

Key Resin Company provides services and consultations on material selection, specification, troubleshooting, and other information on the proper repair and protection of concrete surfaces. **Key Resin Sales/Technical Representatives** are available to assist you. Telephone 888.943.4532 or visit www.keyresin.com.

PHYSICAL PROPERTIES

Tensile Strength	ASTM D638	8,500 psi
Elongation	ASTM D638	5.5%
Compressive Strength	ASTM D695	11,000 psi
Adhesion to Concrete	ASTM D7294	300-400+ psi (Concrete Failure, varies by concrete strength)
Hardness, Shore D	ASTM D2240, 24 hrs	70-80
Abrasion Resistance	ASTM C501 (CS-17 wheel, 1 kg load, 1000 cycles)	70-75 mg loss
Flexural Strength	ASTM D790	8,700 psi
Indentation	MIL-D-3134J	Withstands 2,000 lbs./sq.in. for 30 min. without indentation
Impact Resistance	MIL-D-3134J	Withstands 16ft./lbs. no cracking, delamination or chipping
Elevated Temperature Resistance	MIL-D-313J	No slip or flow at required temperatures at 158°F
Water Absorption	ASTM D-670-63 (24. hr. immersion)	0.10% maximum

WARRANTY

Key Resin Company ("Key") warrants for a period of one (1) year that its products will be free of manufacturing defects and will be in conformity with published specifications when handled, stored, mixed, and applied in accordance with recommendations of Key. If any product fails to meet this warranty, the liability of Key will be limited to replacement of any non-conforming material if notice of such non-conformity is given to Key within (1) one year of delivery of materials. Key may in its discretion refund the price received by Key in lieu of replacing the material. No customer, distributor, or representative of Key is authorized to change or modify the published specifications of this warranty in any way. No one is authorized to make oral warranties on behalf of Key. In order to obtain replacement or refund the customer must provide written notice containing full details of the non-conformity. Key reserves the right to inspect the non-conforming material prior to replacement. EXCEPT FOR THE EXPRESSED WARRANTY STATED ABOVE, THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR PURPOSE. KEY'S OBLIGATION SHALL NOT EXTEND BEYOND THE OBLIGATIONS EXPRESSLY UNDERTAKEN ABOVE AND KEY SHALL HAVE NO LIABILITY OR RESPONSIBILITY TO THE PURCHASER OR ANY THIRD PARTY FOR ANY LOSS, COST, EXPENSE, DAMAGE OR LIABILITY, WHETHER DIRECT OR INDIRECT, OR FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Rev 7/22/2025 v2.3

CORPORATE OFFICE / EASTERN US / INTERNATIONAL

4050 Clough Woods Drive . Batavia, OH 45103
513.943.4225 888.943.4532 www.keyresin.com

WESTERN US

4330 N. 43rd Avenue, Suite B4, Phoenix, AZ 85031
602.523.9353